

## Technical Data Sheet

# Absonet Superior Special

**COMPOSITION:** Calcined Attapulgite

### TECHNICAL INFORMATION

#### PRODUCT INFORMATION

Best before date <sup>1</sup>	5 years
-------------------------------	---------

#### PHYSICO-CHEMICAL PROPERTIES

	Test method <sup>2</sup>	Specifications <sup>3</sup>
Moisture <sup>4</sup> (%)	UNG-009	Max. 5.0
Water absorption <sup>5</sup> (%)	UNG-005	Min. 110
Gasoil absorption <sup>5</sup> (%)	UNG-006	Min. 110
Particle size distribution by dry sieving (%):		
Residue on 1.40 mm	UNG-007	Max. 3.0
Finer than 0.60 mm		Max. 5.0

#### Typical Values<sup>6</sup>

Water absorption <sup>5</sup> (%)	135
Fuel Oil absorption <sup>7</sup> (%)	75
Gasoil absorption <sup>5</sup> (%)	120

(1) From manufacturing date. Stored in dry place protected from humidity and preserved in original package.

(2) Test methods employed in all Tolsa laboratories around the world.

(3) Applicable to the whole batch.

(4) Measured at production point. Moisture can vary according to relative humidity.

(5) According to standard NF T 90-361, and NF P 98-190.

(6) Indicative values. Not specification values.

(7) Absonet Superior Xtra fulfills the standard for oil absorbents LTws-Nr.27, Type IIIIR (tested in DEKRA)

